Contents lists available at ScienceDirect

# **Optical Materials**

journal homepage: www.elsevier.com/locate/optmat

# <sup>60</sup>Co γ-irradiation of AlGaN UVC light-emitting diodes

Xinyi Xia<sup>a</sup>, Sergei Stepanoff<sup>b</sup>, Aman Haque<sup>c</sup>, Douglas E. Wolfe<sup>b</sup>, Simon Barke<sup>d</sup>, Peter J. Wass<sup>d</sup>, Fan Ren<sup>a</sup>, John W. Conklin<sup>d</sup>, S.J. Pearton<sup>e,\*</sup>

<sup>a</sup> Department of Chemical Engineering, University of Florida, Gainesville, FL 32606, USA

<sup>b</sup> Department of Materials Science & Engineering, Penn State University, University Park, PA 16802, USA

<sup>c</sup> Department of Mechanical Engineering, Penn State University, University Park, PA 16802, USA

<sup>d</sup> Department of Mechanical and Aerospace Engineering, University of Florida, Gainesville, FL 32611, USA

<sup>e</sup> Department of Materials Science and Engineering, University of Florida, Gainesville, FL 32606, USA

#### ARTICLE INFO

Keywords: Light-emitting diodes Radiation damage Gamma irradiation Deep UV

### ABSTRACT

270 nm AlGaN UV Light-Emitting Diodes (LEDs) were exposed to 1–5 Mrad fluences of Co-60  $\gamma$ -rays. The effect of the exposure to radiation was a ~40% reduction in optical output after the highest fluence. No significant midgap emission was induced in the electro-luminescence spectra of the irradiated LEDs. We ascribe the decrease in optical output to creation of non-radiative states within the active regions. There were small (5–10%) increases in forward and reverse current as a result of irradiation with an effective carrier removal rate of <1 cm<sup>-1</sup>. The irradiation did not produce any increase in degradation rate of the LEDs output power under high drive current (95 mA) compared to unirradiated devices, which is consistent with the lack of midgap emission. The relatively small changes in electrical and optical properties, along with the resistance of the Al<sub>x</sub>Ga<sub>1-x</sub>N/AlN to displacement damage effects indicate these devices may be well-suited to harsh terrestrial and space radiation applications.

#### 1. Introduction

Deep-UV Light-Emitting Diodes (LEDs) are a promising technology with a wide range of potential applications, including sterilization, water purification, and medical diagnostics [1–5]. These LEDs emit light in the deep-UV wavelength range (230–300 nm), which is strongly absorbed by DNA and RNA, making them effective at inactivating a variety of microorganisms [3–5]. The external quantum efficiency (EQE) of Al<sub>x</sub>Ga<sub>1-x</sub>N-based deep-UV LEDs is typically <0.5%, but this can be improved by optimizing the device structure and fabrication process [6]. Recent advances in deep-UV LED technology have enabled the impressive development of devices with EQEs exceeding 10% [6–15], which is sufficient for many applications [6].

These LEDs have several advantages over conventional UV sources, such as mercury lamps and excimer lasers [1-15]. They are more compact, have a longer lifetime, and can be modulated at much higher frequencies. These LEDs are also expected to have applications in the Laser Interferometer Space Antenna (LISA), the first gravitational wave detector in space, for discharge capability on free-flying test masses to minimize the effect of electrostatic forces caused by cosmic rays and

\* Corresponding author. *E-mail address:* spear@mse.ufl.edu (S.J. Pearton).

https://doi.org/10.1016/j.optmat.2023.114015

Received 27 April 2023; Received in revised form 3 June 2023; Accepted 9 June 2023 Available online 20 June 2023  $0925\text{-}3467/\mathbb{O}$  2023 Elsevier B.V. All rights reserved.

#### solar particles [16-20].

However, there is still much to understand in terms of the response of these materials to various radiation environments, including total ionizing dose conditions where ionization energy deposition dominates and single event upsets during heavy ion strikes [18,21-28]. Sun et al. [18] reported experiments in which UV LEDs were irradiated with  $\sim$ 63 MeV protons to fluences of  $2 \times 10^{12}$  protons/cm<sup>2</sup>, equivalent to ~100 years of radiation dose in the LISA orbit. The light output from the LEDs did not show significant changes. The strong atomic bonding and high defect recombination rates at room temperature are reasons why these materials also display strong resistance to radiation damage displacement effects and highlights their potential for operation in harsh space or terrestrial environments [28]. However, the response to other sources of radiation, including gamma rays, neutrons, and electrons must be established. Radiation damage in photonic devices can cause several problems, including a decrease in the emission intensity, increase in the leakage current and a decrease in the breakdown voltage and creation of defects in the device, such as vacancies and interstitials, which can trap carriers and lead to non-radiative recombination. Wang et al. [21] reported that  $\gamma$  -ray irradiation accelerated degradation caused by





**Research Article** 







**Fig. 1.** (Top) Optical microscope image of packaged UV LED (center) image of device at zero bias and (bottom) small amount of visible light observed under bias in the dark. In the top image the chip area is  $3.5 \times 3.5$  mm<sup>2</sup>.

electrical stress in AlGaN-based UVC LEDs. Typically, UV LED aging rate is inversely proportional to the third power of drive current density [30–36], and part of the degradation in optical output is due to Auger-Meitner recombination, in which electrons and holes recombine across the semiconductor band gap [37]. This leads to a transfer of energy via the Coulomb interaction to another electron or hole, which is excited to a higher energy state.

The presence of resistive layers within the UVC LED raises the question of the possible susceptibility of such devices to ionizing radiation, which can be conveniently studied using gamma rays [38]. Total Ionizing Dose (TID) testing using Co-60  $\gamma$  sources remains the standard test method for space craft instrumentation qualification [39].

The main energy loss mechanism at the energy of Co-60  $\gamma$ -rays is Compton scattering. This can lead to secondary electrons able to displace lattice atoms [40,41]. The primary displacement defects created in AlGaN by gamma-irradiation are Frenkel pairs, produced by these Compton electrons. The Non-Ionizing Energy Loss (NIEL) for gamma rays is much less than for ions, with only a few percent of the gamma photon flux creating secondary Compton electrons.

In this paper we report on the response of UVC LEDs to Co-60 gamma rays. Even to fluences of 5 Mrad, no midgap emission is introduced and only modest decreases in band edge emission are observed. This fluence does not increase the degradation rate of output power under high drive currents.

#### 2. Experimental

The 270 nm packaged LEDs (Klaran LA Series) with peak emission between 260 nm and 270 nm, >80 mW output power and mounted in 3.5 mm  $\times$  3.5 mm surface mount diode packages were purchased from Crystal IS. The basic structure consists of epi layers from by Metal Organic Chemical Vapor Deposition on a (0001) AlN single crystal substrate. The buffer layer is  $\sim 0.5 \ \mu m$  of Al<sub>0.7</sub>Ga<sub>0.3</sub>N, followed by a multi-quantum well structure consisting of pairs of Al<sub>0.58</sub>Ga<sub>0.42</sub>N/ Al<sub>0.7</sub>Ga<sub>0.3</sub>N wells/barriers. There is an electron blocking layer prior to the p-GaN top contact layer. More details are described elsewhere by the supplier [42]. The bowing parameters and emission wavelength for AlGaN QWs as a function of Al composition are described elsewhere [43, 44]. A photograph of one of the LEDs is shown at the top of Fig. 1, while the center and bottom shows the difference in the same device under bias without room illumination to show the almost complete absence of visible emission from midgap states. The current-voltage (I-V) characteristics were recorded with an Agilent 4156C parameter analyzer was used for forward and reverse current and capacitance-voltage (C-V) measurements. The emission spectra were measured using an Avantes AvaSpec-ULS2048XL-EVO spectrometer, which was fiber-coupled the spectrometer to the UV LED with a 600  $\mu$ m diameter fiber optic cable. Total output power measurements were made by coupling the LEDs to a Si photodetector in series with a 55 Ohm resistor, measuring the resistor voltage, and calculating the resultant power. The statistical spread in spectral characteristics of large batches of these LEDs has been reported previously [29,30].

Packaged devices were irradiated by a Co-60 irradiation facility within a 1 MW TRIGA facility at the RSEC, Penn State, with a dose rate of 180 krad/h ( $\pm$ ~10%), resulting in total fluence of 1 or 5 Mrad (Si). The isodose region was used to ensure isotropic gamma dose. The TID was calculated using the relation 1 rad (Si) =  $2.0 \times 10^9$  photons. cm<sup>-2</sup>, which represents the energy lost to ionization over mass. No secondary irradiation was induced in the AlGaN/AlN by Co-60 gamma rays. The LEDs were unbiased during the approximately 30-h exposure, and the generation rate in the AlGaN quantum wells was estimated to be ~10<sup>15</sup> e-h pairs/Gy.cm<sup>3</sup> based on reported threshold energies for pair creation. The gamma rays pass through the entire packages structure, as evidenced from the mean-free path shown in Fig. 2 (top). This was obtained from the EpiXS code for photon attenuation [45]. The linear attenuation coefficients are dominated by Compton scattering for the energies of Co-60  $\gamma$ -rays, as shown at the bottom of Fig. 2 [45].



Fig. 2. (Top) Mean free path of  $\gamma$ -rays as a function of energy in AlN (bottom) linear attenuation coefficients as a function of photon energies. The specific case of specific case of Co-60  $\gamma$ -ray energies are indicated by the vertical lines in both plots.



Fig. 3. Collection of I–V characteristics from 10 different UV LEDs prior to irradiation.

#### 3. Results and discussion

It is important to establish the statistical spread in the initial performance of the LEDs so that the change in performance after irradiation can be quantified. Fig. 3 shows the I–V characteristics of 10 individual devices prior to irradiation, with outliers removed. The spread in their performance is comparable to the radiation-induced changes, so we identified each individual LED and kept track of their characteristics before and after the radiation exposure. We were very careful to compare the same devices before and after irradiation, and that's why we kept track of the individual device number. We therefore feel very confident the changes seen after irradiation are representative. The I-Vs are typical of previously published reports, with turn-on voltages around 4 V [29,30]. Outlier devices can be excluded by selecting for figures of merit, such as the UV power at 1 mA or 20 mA, the ratio of optical power within the main spectral peak to total optical power at low drive currents, reverse leakage current at a drive voltage of -6 V, ideality factor before turn-on, and ideality factor after turn-on [29,30]. The ideality factors are generally >2 due to the presence of multiple current conduction mechanisms [46-48].

Fig. 4 shows the electro-luminescence spectra from a typical LED before and after 1 or 5 Mrad fluence. The panel at top shows the data in linear form, where it is clear the peak intensities have decreased by  $\sim 10$  and 35%, respectively, for 1 and 5 Mrad exposures. Noteworthy is the data in the bottom panel, where the log scale plots reveal there is no increase in the midgap emission from 400 to 600 nm. These transitions are usually ascribed to the presence of deep trap states, which degrade the optical and electrical performance of the LEDs [47,48]. This has important implications for the subsequent aging kinetics of the LEDs, as discussed later. The increase in non-radiative recombination centers in the quantum wells and barriers, and this behavior has been ascribed to Al or Ga vacancy complexes [32–34].

Fig. 5 shows the integrated power from the LEDs as a function of drive current before and after the fluences of 1 Mrad (top) or 5 Mrad (bottom). These were measured by the Si photodetector. The changes in output power support the small changes seen in peak bandedge intensity observed in the spectra.

Fig. 6 shows the I-V characteristics from LEDs before and after



**Fig. 4.** (top) Output spectra from UV LED before and after irradiation with 1 or 5 Mrad fluence (bottom same spectra, shown on log-scale. Note the absence of midgap emission, even after irradiation.

irradiation with either 1 Mrad (top) or 5 Mrad (bottom). Within experimental error, there is no change in the I-V characteristics for the low fluence condition. For the 5 Mrad condition, we were able to find an LED with low initial reverse leakage and that showed an increase in both reverse and forward current after irradiation for voltages <4 V forward and <6 V reverse bias. This is consistent with previous report for devices where their performance was degraded by forward bias stressing [21]. This was ascribed to generation of point defects which form deep levels and act as non-radiative Shockley-Read-Hall recombination centers [32,49,50]. From the reverse bias capacitance change after irradiation, we found the carrier removal rate was <1 cm<sup>-1</sup>. This is consistent with the small amount of displacement damage created by the  $\gamma$ -rays. We want to emphasize that the reverse current increase was only visible in a limited number of LEDs. These were devices with a lower initial reverse leakage, and we were able to see an increase with irradiation. Most devices did not show any significant increase after irradiation because of their higher initial reverse current. We did this to emphasize the



**Fig. 5.** Output power as a function of drive current before and after (top) 1 Mrad fluence or (bottom) 5 Mrad fluence.

relatively small changes induced by even the highest gamma ray fluence.

Fig. 7 shows that the aging characteristics of the LEDs under a high forward current of 95 mA was unaffected within experimental error by the irradiation fluence of 5 Mrad. This is consistent with the low concentration of midgap states evident from the emission spectra after irradiation. Wang et al. [21] reported that  $\gamma$  -irradiation accelerated the degradation of UVC LEDs induced by electrical stress. They employed lower Co-60 fluence of 1.75 Mrad (Si) but did use LEDs grown on sapphire substrates, which will have higher dislocation densities than the devices in this study and may have made the devices more prone to degradation during forward bias stressing. Our results show the benefit of advanced AlN substrates for growth, which improve LED performance (external and internal quantum efficiency) as well as LED lifetime.

#### 4. Summary and conclusions

UVC LEDs grown on AlN substrates show robustness against Co-60  $\gamma\text{-rays}$  to fluences of 5 Mrad (Si) and show their applicability to



**Fig. 6.** I–V characteristics from UV LEDs before and after irradiation with (top) 1 Mrad or (bottom) 5 Mrad.

operation in radiation environments such as space or nuclear plants. The devices show a decrease of  $\sim$ 40% in peak emission intensity as a result of the irradiation, with relatively small changes in the electrical characteristics due to trap-assisted tunnelling. The absence of midgap emission in the unirradiated LEDs is an advantage, since it is clear that a threshold density of midgap states are needed to affect the subsequent aging characteristics and starting with a low number means the introduction of traps by irradiation doesn't reach this threshold.

Given the previously established radiation hardness of UV LEDs to proton irradiation, our results add to the notion that these devices will be well-suited to space-borne applications.

## **CRediT** author statement

Xinyi Xia: Conceptualization, Methodology, Investigation: Sergei Stepanoff, Methodology Aman Haque, Methodology: Douglas E. Wolfe, Methodology: Fan Ren, Methodology, Writing - Reviewing and Editing: Peter J. Wass, Methodology, Writing - Reviewing and Editing: Fan Ren, Methodology, Writing - Reviewing and Editing: John W. Conklin, Methodology, Writing - Reviewing and Editing: S.J. Pearton, Methodology, Writing.



**Fig. 7.** Time dependent peak intensity under forward 95 mA bias for reference (unirradiated) and 5 Mrad fluence exposed LEDs.

#### Declaration of competing interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

#### Data availability

Data will be made available on request.

#### Acknowledgments

This work was supported by NASA Earth Science Technology Office (ESTO) contract 80NSSC22K0288. The work at UF was also performed as part of Interaction of Ionizing Radiation with Matter University Research Alliance (IIRM-URA), sponsored by the Department of the Defense, Defense Threat Reduction Agency under award HDTRA1-20-2-0002. The content of the information does not necessarily reflect the position or the policy of the federal government, and no official endorsement should be inferred. AH also acknowledges support from the US National Science Foundation (ECCS # 2015795). The work at UF was also supported by NSF DMR 1856662.

#### References

- H. Hirayama, Recent progress in AlGaN deep-UV LEDs, in: J. Thirumalai (Ed.), Light-Emitting Diodes, IntechOpen, Rijeka, 2018, 2018, Chap. 7.
- M.S. Shur, R. Gaska, Deep-ultraviolet light-emitting diodes, IEEE Trans. Electron. Dev. 57 (2010) 12–25.
- [3] N. Trivellin, D. Fiorimonte, F. Piva, M. Buffolo, C. De Santi, G. Meneghesso, E. Zanoni, M. Meneghini, Reliability of commercial UVC LEDs: 2022 state-of-theart, Electronics 11 (2022) 728–746.
- W. Kowalski, Ultraviolet Germicidal Irradiation Handbook, Springer, Berlin, Heidelberg, 2009, https://doi.org/10.1007/978-3-642-01999-9.
- [5] H. Inagaki, A. Saito, H. Sugiyama, T. Okabayashi, S. S. Fujimoto, Rapid inactivation of SARS-CoV-2 with deep-UV LED irradiation, Emerg. Microb. Infect. 9 (2020) 1744–1747, https://doi.org/10.1080/22221751.2020.1796529.
- [6] H. Amano, R. Collazo, C. De Santi, S. Einfeldt, M. Funato, J. Glaab, S. Hagedorn, A. Hirano, H. Hirayama, R. Ishii, Y. Kashima, Y. Kawakami, R. Kirste, M. Kneissl, R. Martin, F. Mehnke, M. Meneghini, A. Ougazzaden, P.J. Parbrook, S. Rajan, P. Reddy, F. Römer, J. Ruschel, B. Sarkar, F. Scholz, L.J. Schowalter, P. Shields, Z. Sitar, L. Sulmoni, T. Wang, T. Wernick, M. Weyers, B. Witzigmann, Y.R. Wu, T. Wunderer, Y. Zhang, The 2020 UV emitter roadmap, J. Phys. D Appl. Phys. 53
- (2020), 503001.
  [7] Michael Kneissl, T.Y. Seong, Han, Jung and Amano, Hiroshi, the emergence and prospects of deep-ultraviolet light-emitting diode technologies, Nat. Photonics 13 (2019) 233–244.
- [8] H. Hirayama, Takayoshi Takano, Mino Sakai, Jun, Tsubaki Takuya, Maeda Kenji, Jo Noritoshi, Issei Ohshima Masafumi, Matsumoto Issei, Kamata Takuma, Norihiko, over 10% EQE AlGaN deep-UV LED using transparent p-AlGaN contact layer, in: 2017, Proc. SPIE 10104, 2017, p. 101041.

- [9] Takano, Takayoshi, Mino, Takuya, Jun Sakai, Jun Noguchi, Norimichi, Tsubaki, Kenji and Hirayama, Hideki, Deep-ultraviolet light-emitting diodes with external quantum efficiency higher than 20% at 275 nm achieved by improving lightextraction efficiency 2017, Appl. Phys. Express 10, 031002.
- [10] Max Shatalov, Wenhong Lunev Sun, Alex, Xuhong Hu, Dobrinsky, Alex, Yuri Bilenko, Jinwei Yang, Michael Shur, Gaska, Remis, Craig Moe, Gregory Garrett, Michael Wraback, AlGaN deep-ultraviolet light-emitting diodes with external quantum efficiency above 10, Appl. Phys. Express 5 (2012), 082101.
- [11] Masatsugu Fujioka Ichikawa, Kosugi Akira, Endo Takao, Sagawa Shinya, Harunobu Harunobu, Hiroto Mukai Tamaki, Uomoto Miyuki Takashi, Takehito Shimatsu, High-output-power deep ultraviolet light-emitting diode assembly using direct bonding, Appl. Phys. Express 9 (2016), 072101.
- [12] J. Zhang, Y. Gao, L. Zhou, Y.-U. Gil, K.-M. Kim, Transparent deep ultraviolet lightemitting diodes with a p-type AlN ohmic contact layer, in: Proc. SPIE 10940, Light. Devices, Mater. Appl. 1094002-1, 2019.
- [13] Y. Matsukura, T. Inazu, C. Pernot, N. Shibata, M. Kushimoto, M. Deki, Y. Honda, H. Amano, Improving light output power of AlGaN-based deep-ultraviolet lightemitting diodes by optimizing the optical thickness of p-layers, 2021, Appl. Phys. Express 14 (2021), 084004.
- [14] Zhang Jianping, Gao, Ying Zhou, Ling Gil, Gil Young-Un, Kim Kyoung-Min Kim, Surface hole gas enabled transparent deep ultraviolet light-emitting diode, Semicond. Sci. Technol. 33 (2018), 07LT01.
- [15] Y. Nagasawa, A. Hirano, A review of AlGaN-based deep-ultraviolet light-emitting diodes on sapphire, Appl. Sci. 8 (2018) 1264–1300.
- [16] D. Hollington, J.T. Baird, T.J. Sumner, P.J. Wass, Characterizing and testing deep UV LEDs for use in space applications, Classical Quant. Grav. 32 (2015), 235020.
- [17] P.J. Wass, H.M. Araújo, D.N.A. Shaul, T.J. Sumner, Test-mass charging simulations for the LISA pathfinder mission, Classical Quant. Grav. 22 (2005) S311–S317.
- [18] K.X. Sun, N. Leindecker, S. Higuchi, J. Goebel, S. Buchman, R.L. Byer, L. R, UV LED operation lifetime and radiation hardness qualification for space flights, J. Phys. Conf. Ser. 154 (2009), 012028-1-012028-6.
- [19] S. Saraf, S. Buchman, K. Balakrishnan, C.Y. Lui, M. Soulage, D. Faied, J. Hanson, K. Ling, B. Jaroux, B.A. Suwaidan, A. AlRashed, B. Al-Nassban, F. Alaqeel, M. A. Harbi, B.B. Salamah, M.B. Othman, B.B. Qasim, A. Alfauwaz, M. Al-Majed, D. DeBra, Ground testing and flight demonstration of charge management of insulated test masses using UV LED electron photoemission, Classical Quant. Grav. 33 (2016), 245004.
- [20] P.J. Wass, LISA Pathfinder Collaboration, Free-fall performance for the LISA gravitational wave observatory: new results from LISA pathfinder, in: APS April Meeting 2018 (2018), vol. 2018, 2018 p. C14.001. Available at: http://meetings. aps.org/link/BAPS.2018.APR.C14.1 (accessed on 4/12/2023).
- [21] Y. Wang, X. Zheng, J. Zhu, Y. Cao, X. Wang, T. Zhu, L. Lv, W. Mao, C. Wang, X. Ma, P. Li, N. Hua, K. Chen, M. Wang, Q. Zhang, Y. Hao, Gamma-irradiation-accelerated degradation in AlGaN-based UVC LEDs under electrical stress, IEEE Trans. Nucl. Sci. 68 (2021) 149–155.
- [22] M.W. Moseley, A.A. Allerman, M.H. Crawford, J.J. Wierer, M.L. Smith, A. M. Armstrong, M. A, Detection and modeling of leakage current in AlGaN-based deep ultraviolet light-emitting diodes, J. Appl. Phys. 117 (2015), 095301-1–095301-7, Mar. 2015.
- [23] A. Floriduz, J.D. Devine, Modelling of proton irradiated GaN-based high-power white light-emitting diodes, Jpn. J. Appl. Phys. 57 (2018), 080304-1–080304-5.
- [24] I.H. Lee, A.Y. Polyakov, N.B. Smirnov, I.V. Shchemerov, P.B. Lagov, R.A. Zinov'Ev, E.B. Yakimov, K.D. Shcherbachev, S.J. Pearton, Point defects controlling nonradiative recombination in GaN blue light emitting diodes: insights from radiation damage experiments, J. Appl. Phys. 122 (2017), 115704-1–115704-6.
- [25] I.H. Lee, A.Y. Polyakov, I.V. Smirnov, Shchemerov, N.M. Shmidt, N.A. Tal'nishnih, E.I. Shabunina, H.S. Cho, S.M. Hwang, R.A. Zinovyev, S.I. Didenko, P.B. Lagov, S. J. Pearton, Electron irradiation of near-UV GaN/InGaN light emitting diodes, Phys. Status Solidi A 214 (2017), 1700372-1–1700372-5.
- [26] R. Khanna, S.Y. Han, S.J. Pearton, D. Schoenfeld, W.V. Schoenfeld, F. Ren, High dose Co-60 gamma irradiation of InGaN quantum well light-emitting diodes, Appl. Phys. Lett. 87 (2005), https://doi.org/10.1063/1.2132085, 212107-1–212107-3.
- [27] B. Luo, J.W. Johnson, F. Ren, K.K. Allums, C.R. Abernathy, S.J. Pearton, A. M. Dabiran, M. A, A. Wowchack, C.J. Polley, P.P. Chow, D. Schoenfeld, A.G. Baca, Influence of 60 Co γ -rays on dc performance of AlGaN/GaN high electron mobility transistors, Appl. Phys. Lett. 80 (2002) 604–606, https://doi.org/10.1063/ 1.1445809.
- [28] S.J. Pearton, F. Ren, E. Patrick, M.E. Law, A.Y. Polyakov, Review-ionizing radiation damage effects on GaN devices, ECS J. Solid State Sci. Technol. 5 (2015), https:// doi.org/10.1149/2.0251602jss. Q35–Q60-96.
- [29] B.C. Letson, S. Barke, P. Wass, G. Mueller, F. Ren, S.J. Pearton, J.W. Conklin, Deep UV AlGaN LED reliability for long duration space missions, J. Vac. Sci. Technol. A 41 (2023), 013202, https://doi.org/10.1116/6.0002199.
- [30] B.C. Letson, S. Barke, S.P. Kenyon, T. Olatunde, G. Mueller, P. Wass, F. Ren, S. J. Pearton, J.W. Conklin, High volume UV LED performance testing, Rev. Sci. Instrum. 93 (2022), 114503, https://doi.org/10.1063/5.0107372.
- [31] A. Yoshikawa, R. Hasegawa, T. Morishita, K. Nagas, S. Yamada, J. Grandusky, J. Mann, A. Amy Miller, L.J. Schowalter, Improve efficiency and long lifetime UVC LEDs with wavelengths between 230 and 237 nm, Appl. Phys. Express 13 (2020), 022001, https://doi.org/10.35848/1882-0786/ab65fb.
- [32] M. Buffolo, A. Caria, F. Piva, N. Roccato, C. Casu, C. De Santi, N. Trivellin, G. Meneghesso, E. Zanoni, Matteo Meneghini, Defects and reliability of GaN-based LEDs: review and perspectives, Phys. Status Solidi A 219 (2022), 2100727, https:// doi.org/10.1002/pssa.202100727.
- [33] N. Trivellin, D. Fiorimonte, F. Piva, M. Buffolo, C. De Santi, G. Meneghesso, E. Zanoni, M. Meneghini, Reliability of commercial UVC LEDs: 2022 state-of-the-

#### X. Xia et al.

art, Electronics 11 (2022) 728–733, https://doi.org/10.3390/electronics11050728.

- [34] D. Monti, M. Meneghini, C. De Santi, G. Meneghesso, E. Zanoni, J. Glaab, J. Rass, S. Einfeldt, F. Mehnke, J. Enslin, T. Wernicke, M. Kneiss, Defect-related degradation of AlGaN-Based UV-B LEDs, IEEE Trans. Electron. Dev. 64 (2017), https://doi.org/10.1109/TED.2016.2631720, 200–5.
- [35] Z. Ma, H. Cao, S. Lin, X. Li, L. Zhao, Degradation and failure mechanism of AlGaNbased UVC-LEDs, Solid State Electron. 156 (2019) 92–96, https://doi.org/ 10.1016/j.sse.2019.01.004.
- [36] F. Piva, C. De Santi, M. Deki, M. M.Kushimoto, H. H.Amano, H. Tomozawa, N. Shibata, G. Meneghesso, E. Zanoni, M. M. Meneghini, Modeling the degradation mechanisms of AlGaN-based UV-C LEDs: from injection efficiency to mid-gap state generation, Photonics Res. 8 (2020) 1786, https://doi.org/10.1364/prj.401785.
- [37] D. Matsakis, A. Coster, B. Laster, R. Sime, A renaming proposal, 2019, the Auger-Meitner effect, Phys. Today 72 (9) (2019) 10–11, https://doi.org/10.1063/ PT.3.4281.
- [38] G.P. Summers, E.A. Burke, P. Shapiro, S.R. Messenger, R.J. Walters, Damage correlations in semiconductors exposed to gamma, electron and proton radiations, IEEE Trans. Nucl. Sci. 40 (1993) 1372, https://doi.org/10.1109/23.273529.
- [39] Total dose steady-state irradiation test method," European space components, coordination basic specification No. 22900. http://escies.org/escc-specs/publishe d/22900.pdf, 2016.
- [40] E. El Allam, C. Inguimbert, A. Meulenberg, A. Jorio, I. Zorkani, J. Appl. Phys. 123 (2018), 095703.
- [41] D.M. Fleetwood, IEEE Trans. Nucl. Sci. 60 (2013) 1706-1712.
- [42] Leo Schowalter, Pseudomorphic AlGaN Semiconductor: from UVC LED and UVC Laser Diodes to Rf and Power Revolution, Available at:, IEEE EDS Webinar, 2020 https://ieee.webex.com/recordingservice/sites/ieee/recording/00f9b8cfe96e40e db0c600f1cafa4a11/playback.

- [43] J.R. Grandusky, Shawn R. Gibb, C. Mendrick Mark, Craig Moe, Michael Wraback, Leo J. Schowalter, High output power from 260 nm pseudomorphic ultraviolet light-emitting diodes with improved thermal performance, Applied Physics Express 3 (2010), 072103, https://doi.org/10.1143/APEX.4.082101.
- [44] Y.A. Goldberg, Semiconductor near-ultraviolet photoelectronics, Semicond. Sci. Technol. 14 (1999) 41, https://doi.org/10.1088/0268-1242/14/7/201.
- [45] F.C. Hila, A. Asuncion-Astronomo, C.A.M. Dingle, J.F.M. Jecong, A.M.V. Javier-Hila, M.B.Z. Gili, C.V. Balderas, G.E.P. Lopez, N.R.D. Guillermo, A.V. Amorsolo, EpiXS: a Windows-based program for photon attenuation, dosimetry and shielding based on EPICS2017 (ENDF/B-VIII) and EPDL97 (ENDF/B-VI.8), Radiat. Phys. Chem. 182 (2021), 109331, https://doi.org/10.1016/j. radphyschem.2020.109331.
- [46] H. Masui, Diode ideality factor in modern light-emitting diodes, Semicond. Sci. Technol. 26 (2011), 075011, https://doi.org/10.1088/0268-1242/26/7/075011.
- [47] J.M. Shah, Y.L. Li, T. Gessmann, E.F. Schubert, Experimental analysis and theoretical model for anomalously high ideality factors (n≫2.0) in AlGaN/GaN p-n junction diodes, J. Appl. Phys. 94 (2003) 2627, https://doi.org/10.1063/ 1.1593218.
- [48] H. Masui, S. Nakamura, S.P. DenBaars, Technique to evaluate the diode ideality factor of light-emitting diodes, Appl. Phys. Lett. 96 (2010), 073509, https://doi. org/10.1063/1.3318285.
- [49] S.F. Chichibu, A. Uedono, K. Kojima, H. Ikeda, K. Fujito, S. Takashima, M. Edo, K. Ueno, S. Ishibashi, The origins and properties of intrinsic nonradiative recombination centers in wide bandgap GaN and AlGaN, J. Appl. Phys. 123 (2018), 161413, https://doi.org/10.1063/1.5012994.
- [50] H. Nykänen, S. Suihkonen, L. Kilanski, M. Sopanen, F. Tuomisto, Low energy electron beam induced vacancy activation in GaN, Appl. Phys. Lett. 100 (2012), 122105, https://doi.org/10.1063/1.3696047.